

SURAT KETERANGAN

Nomor: 520/UNUSA/Adm-LPPM/V/2021

Lembaga Penelitian dan Pengabdian Kepada Masyarakat (LPPM) Universitas Nahdlatul Ulama Surabaya menerangkan telah selesai melakukan pemeriksaan duplikasi dengan membandingkan artikel-artikel lain menggunakan perangkat lunak **Turnitin** pada tanggal 09 Maret 2021.

Judul : *Cytotoxicity Assay Using Brine Shrimp Lethality Test on Collagen-Chitosan Wound Dressing Sterilized by Ultraviolet Light*

Penulis : Ary Andini, Endah Prayekti, Devyana Dyah Wulandari, Ersalina Nidianti

Identitas : *Indonesian Journal of Medical Laboratory Science and Technology, Vol. 2, No. 1, 2020*

No. Pemeriksaan : 2021.05.11.255

Dengan Hasil sebagai Berikut:

Tingkat Kesamaan diseluruh artikel (*Similarity Index*) yaitu 2%

Demikian surat keterangan ini dibuat untuk digunakan sebagaimana mestinya.

Surabaya, 11 Mei 2021

Ketua LPPM



UNUSA
LPPM

Achmad Syafiuddin, Ph.D

NPP: 20071300

Cytotoxicity Assay Using Brine Shrimp Lethality Test on Collagen- Chitosan Wound Dressing Sterilized by Ultraviolet Light

by Devyana Wulandari

Submission date: 09-Mar-2021 02:17AM (UTC-0800)

Submission ID: 1528289853

File name: Artikel_2020_IJMLST.pdf (319.18K)

Word count: 2232

Character count: 11149

Cytotoxicity Assay Using Brine Shrimp Lethality Test on Collagen-Chitosan Wound Dressing Sterilized by Ultraviolet Light

Ary Andini¹, Endah Prayekti¹, Devyana Dyah Wulandari¹, Ersalina Nidianti¹

¹Department of Medical Laboratory Technology, Faculty of Health, Universitas Nahdlatul Ulama Surabaya, Surabaya, Indonesia

Correspondence:

Ary Andini,
Jl. Jemursari No. 51-57, Surabaya,
East Java, Indonesia
Zip Code : 60237

Email: aryandini@unusa.ac.id

Received: February 14, 2020

Revised: February 17, 2020

Accepted: March 23, 2020



Abstract

Collagen gives a moist state on the wound area to accelerate the wound healing process. Chitosan is a polymer known as non-toxic, antibacterial, antifungal, biodegradable, and biocompatible material. Combination of collagen and chitosan is expected to be the best biomaterials as a wound dressing for the healing process. The study aimed to determine the cytotoxicity assay on collagen-chitosan wound dressing sterilized by ultraviolet (UV) Light using Brine Shrimp Lethality Test (BSLT) method. The test groups were divided into K0, K1, K2, and K3 groups. K0 contained pure chitosan as a control group, K1 contained collagen 25%-chitosan 75%, K2 contained collagen 50%-chitosan 50%, K3 contained collagen 75%-Chitosan 25%. Collagen was extracted from the skin and scalp of snakehead fish (*Channa striata*), then it was mixed with chitosan until collagen-chitosan wound dressing formed. This study used Brine Shrimp Level Test (BSLT) method with solution concentration: 10, 50, 100, 250, 500, 750 and 1000 ppm. Based on the results, it showed that K0, K1, K2, and K3 group had $LC_{50} > 1000$, proved that collagen-chitosan wound dressing was non-toxic material. The conclusion of the study explain that composite wound dressing based on collagen-chitosan in all groups that was sterilized under UV-Light for 15 minutes was not toxic. Also, it showed $LC_{50} > 1000$ based on Brine Shrimp Lethality Test.

Keywords

Collagen, chitosan, BSLT, wound dressing, ultraviolet

INTRODUCTION

There are two kinds of wound dressing, such as traditional wound dressing including gauze, plasters, lint, bandages, cotton wool, and modern wound dressing including films, hydrogel, hydrocolloids, foam and composites (1,2). Wound dressing application

has main roles in healing the wound and preventing infection on wound area. Best wound dressing with good quality could accelerate the wound healing, prevent the wound from infection of bacteria and fungal, and reduce pains (2). The particular wound dressing can promote a newly epithelium

layer that may not be damaged during the dressing removal around the wound (3). The composite dressing is made from a combination of any kind of materials for dressing. It is suitable to burn wounds, surgical wounds, infectious wound and refractory chronic wound (2).

Collagen and chitosan are known as biomaterials that have bioproperties including biocompatible and biodegradable (4). Therefore, it can be developed into composite dressing for wound healing. However, its application is limited due to clinical test before using for human. Few steps were needed before clinical test of a wound dressing which are toxicity (5), quality (6), in vitro and in vivo evaluation test (7).

Based on Ariyadi and Dewi (8) study, it showed that dry sterilization using ultraviolet (UV) irradiation for 10 and 15 minutes would not be contaminated by *Bacillus subtilis* colony (8). Therefore, this research used composite collagen-chitosan extracted from *Channa striata* collagen that was sterilized under ultraviolet (UV) light for 15 minutes to determine LC_{50} using Brine Shrimp Lethally Test (BSLT). Previously, the brine shrimp was utilized in various bioassay such as analysis of pesticide residues, stream pollutant, anesthetics, dinoflagellate toxins, mycotoxins, cocarcinogenicity of phorbol esters, and toxicants in marine (9).

MATERIALS AND METHODS

Skin and scales of sneakhead fish were collected from Srikandi fishmonger at Banjar Asri Village, Tanggulangin Sub-District, Sidoarjo, East Java Province, Indonesia. The 100 mesh Chitosan powder (food and medical grade) was made from black tiger shrimp shells and it was obtained from Monodon (Marine Natural Product). The cytotoxicity assay was conducted by using *Artemia salina* (Golden West Artemia, Supreme Plus).

The collagen was extracted from the skin and scales of sneakhead fish by macerating it in HCl 2% for 48 hours and it was neutralized with NaOH 1M. Chitosan powder was dissolved in CH_3COOH 1% (4). Collagen-chitosan composite was synthesized by mixing collagen 25% : chitosan 75% as K1 group; collagen 50% : chitosan 50% as K2 group; collagen 75% and chitosan 25% as K3 group; and pure chitosan as a control group (K0).

The cytotoxicity assay was carried out with the Brine Shrimp Lethally Test (BSLT) by using *A. salina*. Each collagen-chitosan composite of K0, K1, K2 and K3 was dissolved with DMSO 1 % then was divided into 10 ppm, 50 ppm, 100 ppm, 250 ppm, 500 ppm, 750 ppm and 1000 ppm. As much as 5 mL of each concentration was added into petri dish then it was added with 5 ml of seawater contained in ten *A. salina*. Hereafter, it was incubated for 24 hours (10).

$$\% \text{ Mortality} = \frac{\text{Total Larvae Mortality}}{\text{Total Larvae}} \times 100 \%$$

LC₅₀ assessment was analyzed by Microsoft excel with Probit analysis. Afterward, the toxicity categories of each sample could be determined based on the Table 1.

Table 1. LC₅₀ categories (9)

Categories	LC50 (ppm)
Very Toxic	<30
Toxic	30-1000
Non-Toxic	> 1000

(Source: Meyer *et al*, 1982)

RESULTS

Brine Shrimp Lethally Test (BSLT) was conducted using *Artemia saline* larvae to study the toxicity of collagen-chitosan composite. This study was a preliminary test before the composite applied *in vivo*. The result of probit analysis of larvae mortality percentage for each group sample can be seen in Table 2, 3, 4, and 5.

Table 2. Percentage of Larvae Mortality in K0 Group

Concentration (ppm)	Log 10	Mortality	Total Larvae	% Mortality	Probit
10	1,00	0	10	0%	-
50	1,70	3	10	30%	4,48
100	2,00	0	10	0%	-
250	2,40	0	10	0%	-
500	2,70	1	10	10%	3,72
750	2,88	0	10	0%	-
1000	3,00	0	10	0%	-

Table 3. Percentage of Larvae Mortality in K1 Group

Concentration (ppm)	Log 10	Mortality	Total Larvae	% Mortality	Probit
10	1,00	0	10	0%	-
50	1,70	0	10	0%	-
100	2,00	1	10	10%	3,72
250	2,40	2	10	20%	4,16
500	2,70	1	10	10%	3,72
750	2,88	0	10	0%	-
1000	3,00	2	10	20%	4,16

Table 4. Percentage of Larvae Mortality in K2 Group

Concentration (ppm)	Log 10	Mortality	Total Larvae	%Mortality	Probit
10	1,00	3	10	30%	4,48
50	1,70	1	10	10%	3,72
100	2,00	0	10	0%	-
250	2,40	2	10	20%	4,16
500	2,70	2	10	20%	4,16
750	2,88	2	10	20%	4,16
1000	3,00	0	10	0%	-

Table 5. Percentage of Larvae Mortality in K3 Group

Concentration (ppm)	Log 10	Mortality	Total Larvae	%Mortality	Probit
10	1,00	2	10	20%	4,16
50	1,70	0	10	0%	-
100	2,00	0	10	0%	-
250	2,40	0	10	0%	-
500	2,70	1	10	10%	3,72
750	2,88	3	10	30%	4,48
1000	3,00	1	10	10%	3,72

Tabel 6. LC₅₀ Assesment

No.	Group	LC ₅₀	Toxicity
1	K0	> 1000	Non-Toxic
2	K1	> 1000	Non-Toxic
3	K2	> 1000	Non-Toxic
4	K3	> 1000	Non-Toxic

(Source: Meyer *et al.*, 1982)

Based on the results, it showed that collagen-chitosan composite sterilized by UV light was not toxic. This is based on the interpretation of the data, according to Meyer *et al.*, (9).

DISCUSSION

The composit dressing is used for wound treatment to reduce the contamination risk. The research about wound dressing had developed rapidly due to the demand for

wound treatment which increase every year. Chitosan and collagen are popular biomaterials for wound dressing because of its bioproperties. Sterilization of materials before in vivo assay must be done to prevent microbial and fungal contamination. The UV Light exposure on materials could maintain sterility of materials. However, not every material suitable for this methods. Therefore, cytotoxicity assay has to be conducted to analyse its bioproperties before it used for humans. Brine Shrimp Lethally Test was a

simple cytotoxicity assay by using *A. salina* to obtain LC_{50} . If LC_{50} value is more than 1000, it means that the materials tested were not toxic (9).

Based on the results of the study, it showed that wound dressing for skin wound healing that sterilized by UV light at the whole group was not toxic because $LC_{50} > 1000$. Chitosan was also known as anti-bacterial and anti-fungal properties (4). Exposure of UV sterilization used was 254 nm to inactivate the microbe. Absorption of UV light on microbe could damage nucleic acids and their constituents that caused mutagenetic effect and cell retardation (11). Ultra-Violet (UV) radiation on the material causes chemical modification of nucleoprotein compounds and occurs the cross-linked of timin molecules that could generate false genetic code, promoting mutation that will cause the damage and weaken the vital functions of the organism until dead (8).

Based on the results of Ariyadi and Dewi (8) study, it showed that the best UV method as anti-bacterial treatment was obtained in 10 and 15 minutes. Therefore, this study was using 15 minute for UV exposure as a sterilization method on the wound dressing. Collagen could heal chronics wound by stimulating fibroblast and promoting endogenous collagen synthesis on wound area (12). Based on Lei et al. (12) research, it showed that collagen hydrogel dressing could

promote the rate and quality of diabetic full-thickness wound healing on rats. Moreover, collagen from snakehead fish contains glycine, glutamine and arginine. Glycine has a role in collagen synthesis around the wound area, while glutamine has a role as an energy source during the inflammatory phase and proliferation phase of wound healing. Arginine has a role in immunity system and stimulates endothelial cell function. A chitosan was known as a biomaterial for drug release on wound area due to its hydrogels properties (13). Therefore, the combination of collagen and chitosan can enhance the bioproperties of collagen-chitosan composite dressing.

CONCLUSIONS

Collagen-chitosan based composite wound dressing in all groups (K0, K1, K2 and K3) that was sterilized under UV-Light for 15 minutes were not toxic based on Brine Shrimp Lethally Test which showed $LC_{50} > 1000$.

ACKNOWLEDGEMENTS

The authors gratefully acknowledge the financial supports of this research from the Institute of Research and Community Development of Universitas Nahdlatul Ulama.

CONFLICT OF INTEREST

There are no conflicts of interest.

REFERENCES

1. Dhivya S, Vijaya V, Santhini E. Review article Wound dressings – a review. *BioMedicine*. 2015;5(4):24–8.
2. Lei J, Sun L, Li P, Zhu C, Lin Z, Mackey V, et al. The Wound Dressings and Their Applications in Wound Healing and Management. *Heal Sci J*. 2019;13:1–8.
3. Shabunin AS, Yudin VE, Dobrovolskaya IP, Zinovyev E V, Zubov V, Ivan EM, et al. Chitin / Chitosan Nanofibers: Processing and Biomedical Applications. *Cosmetics*. 2019;6:1–10.
4. Andini A, Prayekti E. Chitosan as Antifungal in *Channa striata* Collagen-Chitosan for Wound Healing. *Med Heal Sci J*. 2019;3(2):8–11.
5. Leliani HN, Seniwati DS. Collagen Extraction from Bone Of *Lutjanus Sp.* and Toxicity Assay. *Indones Chim Acta*. 2019;12(1):67–72.
6. Mennini N. Quality of wound dressings: A first step in establishing shared Criteria and objective procedures to evaluate their performance. *J Wound Care*. 2016;25(October 2017).
7. Kumar PTS, Lakshmanan V, Anilkumar T V, Ramya C, Reshmi P, Unnikrishnan AG, et al. Retraction of “Flexible and Microporous Chitosan Hydrogel/Nano ZnO Composite Bandages for Wound Dressing: In Vitro and In Vivo Evaluation.” *ACS Appl Mater Interfaces*. 2019;11:28596.
8. Ariyadi T, Dewi SS. Pengaruh Sinar Ultra Violet terhadap Pertumbuhan Bakteri *Bacillus sp.* sebagai Bakteri Kontaminan (Effect of Ultra Violet Rays on the Growth of *Bacillus sp.* as Contaminant Bacteria). *J Kesehatan*. 2009;2:20–5.
9. B.N Meyer, N.R. Ferrigni, J.E Putnam, L.B Jacobsen, D.E Nichols J. M. Brine Shrimp : A Convenient General Bioassay for Active Plant Constituents. *J Med Plant Res*. 1982;45:31–4.
10. Muaja AD, Koleangan HSJ, Runtuwene MRJ. Uji Toksisitas dengan Metode BSLT dan Analisis Kandungan Fitokimia Ekstrak Daun Soyogik (*Saurauia bracteosa DC*) dengan Metode Soxhletasi (Toxicity Assay using BSLT Method and Phytochemical Content Analysis of Soyogik Leaf Extract (*Saurauia bracteosa DC*) using Soxhletation Method). *J MIPA Unsrat Online* 2. 2013;2(2):115–8.
11. Antonio C, Silva DS, Andrade NJ De, Fátima N De, Soares F, Ferreira SO. Evaluation of Ultraviolet Radiation to Control Microorganisms Adhering to Low-Density Polyethylene Films. *Brazilian J Microbiol*. 2003;34(1517–8382):175–8.
12. Lei J, Chen P, Li Y, Wang X, Tang S. Collagen hydrogel dressing for wound healing and angiogenesis in diabetic rat models. *Int J Clin Exp Med*. 2017;10(12):16319–27.
13. Ou A, Louis H, Pi A, Oc A, Ei N, Ef O. Biochemistry & Pharmacology : Open Access The Chemistry of Chitin and Chitosan Justifying their Nanomedical Utilities. *Biochem Pharmacol (Los Angel)*. 2018;7(1):1–6.

Cytotoxicity Assay Using Brine Shrimp Lethality Test on Collagen- Chitosan Wond Dressing Sterilized by Ultraviolet Light

ORIGINALITY REPORT

2%

SIMILARITY INDEX

0%

INTERNET SOURCES

2%

PUBLICATIONS

0%

STUDENT PAPERS

PRIMARY SOURCES

1

G Pasaribu, T K Waluyo, I Winarni.

"Phytochemical content, toxicity and antioxidant activities of native medicinal plants from North Sumatra", IOP Conference Series: Earth and Environmental Science, 2020

Publication

2%

Exclude quotes Off

Exclude bibliography Off

Exclude matches Off